

**Technical Data Sheet: GlassX™ Glass-Fiber PETG 3D Printing Filament**

Physical Properties	Standard	Unit	Typical Value
Density	ISO 1183	g/cc	1.41

Mechanical Properties	Standard	Unit	Typical Value
Tensile Strength, Break	ISO 527	MPa	55
Tensile Modulus	ISO 527	MPa	3285
Tensile Elongation, Break	ISO 527	%	4
Flexural Strength	ISO 178	MPa	77
Flexural Modulus	ISO 178	MPa	3320

Thermal Properties	Standard	Unit	Typical Value
Glass Transition Temperature (Tg)	DSC	°C	80
Deflection Temperature at 0.45 MPa (66psi)	ISO 75	°C	70

Electrical Property	Standard	Unit	Typical Value
Surface Resistance	ASTM D257	Ohm/sq	>10 <sup>13</sup>

Printed Specimen Conditions
Printer: Open Source FDM/FFF
Nozzle: 0.4mm
Layer Height: 0.25mm
Infill: 100%, +/- 45°
Extrusion Temp: 255°C
Bed Temp: 70°C
Specimen Orientation: XY Flat